

# Molybdenum, Annealed | MECHANICAL AND PHYSICAL PROPERTIES

	Metric	English
<b>Physical Properties</b>		
Density	10.22 g/cc	0.3692 lb/in <sup>3</sup>
a Lattice Constant	3.147 Å	3.147 Å
	@Temperature 25.0 °C	@Temperature 77.0 °F
Molecular Weight	95.94 g/mol	95.94 g/mol
Melting Point	2617 °C	4743 °F
Boiling Point	4639 °C	8382 °F
<b>Chemical Properties</b>		
Atomic Mass	95.94	95.94
Atomic Number	42	42
Atomic Volume	1.53E-29	1.53E-29
Thermal Neutron Cross Section	2.5 barns/atom	2.5 barns/atom
X-ray Absorption Edge	0.61977 Å	0.61977 Å
	4.32066 Å	4.32066 Å
	4.7133 Å	4.7133 Å
	4.9093 Å	4.9093 Å
Electrode Potential	-0.200 V	-0.200 V
Electronegativity	2.16	2.16
Ionic Radius	0.620 Å	0.620 Å
	0.700 Å	0.700 Å
	0.930 Å	0.930 Å
Electrochemical Equivalent	1.79 g/A/h	1.79 g/A/h
<b>Mechanical Properties</b>		
Hardness, Brinell	225	225
Hardness, Rockwell A	60	60
Hardness, Rockwell B	98	98
Hardness, Rockwell C	19	19
Hardness, Vickers	230	230
Tensile Strength, Ultimate	324 MPa	47000 psi
	350 MPa	50800 psi
Modulus of Elasticity	330 GPa	47900 ksi
	160 GPa	23200 ksi
	@Temperature 2000 °C	@Temperature 3630 °F
	200 GPa	29000 ksi
@Temperature 1800 °C	@Temperature 1800 °C	@Temperature 3270 °F
	250 GPa	36300 ksi
@Temperature 1400 °C	@Temperature 1400 °C	@Temperature 2550 °F
	275 GPa	39900 ksi
	@Temperature 1000 °C	@Temperature 1830 °F
Compressive Yield Strength	400 MPa	58000 psi
Bulk Modulus	272 GPa	39500 ksi
Poissons Ratio	0.38	0.38
Shear Modulus	120 GPa	17400 ksi
Shear Strength	500 MPa	72500 psi

## Electrical Properties

Electrical Resistivity	0.00000570 ohm-cm	0.00000570 ohm-cm
	0.00000520 ohm-cm	0.00000520 ohm-cm
	@Temperature 0.000 °C	@Temperature 32.0 °F
	0.00000570 ohm-cm	0.00000570 ohm-cm
	@Temperature 27.0 °C	@Temperature 80.6 °F
	0.0000239 ohm-cm	0.0000239 ohm-cm
	@Temperature 727 °C	@Temperature 1340 °F
	0.0000292 ohm-cm	0.0000292 ohm-cm
	@Temperature 927 °C	@Temperature 1700 °F
	0.0000352 ohm-cm	0.0000352 ohm-cm
	@Temperature 1127 °C	@Temperature 2061 °F
	0.0000412 ohm-cm	0.0000412 ohm-cm
	@Temperature 1327 °C	@Temperature 2421 °F
	0.0000472 ohm-cm	0.0000472 ohm-cm
	@Temperature 1527 °C	@Temperature 2781 °F
	0.0000535 ohm-cm	0.0000535 ohm-cm
	@Temperature 1727 °C	@Temperature 3141 °F
	0.0000595 ohm-cm	0.0000595 ohm-cm
	@Temperature 1927 °C	@Temperature 3501 °F
	0.0000660 ohm-cm	0.0000660 ohm-cm
	@Temperature 2127 °C	@Temperature 3861 °F
	0.0000692 ohm-cm	0.0000692 ohm-cm
	@Temperature 2227 °C	@Temperature 4041 °F
	0.0000718 ohm-cm	0.0000718 ohm-cm
	@Temperature 2327 °C	@Temperature 4221 °F
	0.0000782 ohm-cm	0.0000782 ohm-cm
	@Temperature 2527 °C	@Temperature 4581 °F
	0.0000814 ohm-cm	0.0000814 ohm-cm
	@Temperature 2622 °C	@Temperature 4752 °F
Magnetic Susceptibility	9.30E-07	9.30E-07
Critical Magnetic Field Strength, Oersted	93 – 99	93 – 99
Critical Superconducting Temperature	0.910 – 0.920 K	0.910 – 0.920 K

## Thermal Properties

Heat of Fusion	293 J/g	126 BTU/lb
Heat of Vaporization	5610 J/g	2410 BTU/lb
CTE, linear	5.35 $\mu\text{m}/\text{m} \cdot ^\circ\text{C}$	2.97 $\mu\text{in}/\text{in} \cdot ^\circ\text{F}$
	@Temperature 20.0 °C	@Temperature 68.0 °F
	6.00 $\mu\text{m}/\text{m} \cdot ^\circ\text{C}$	3.33 $\mu\text{in}/\text{in} \cdot ^\circ\text{F}$
	@Temperature 0.000 – 250 °C	@Temperature 32.0 – 482 °F
	6.00 $\mu\text{m}/\text{m} \cdot ^\circ\text{C}$	3.33 $\mu\text{in}/\text{in} \cdot ^\circ\text{F}$
	@Temperature 0.000 – 500 °C	@Temperature 32.0 – 932 °F
Specific Heat Capacity	6.50 $\mu\text{m}/\text{m} \cdot ^\circ\text{C}$	3.61 $\mu\text{in}/\text{in} \cdot ^\circ\text{F}$
	@Temperature 0.000 – 1000 °C	@Temperature 32.0 – 1830 °F
	0.217 J/g-°C	0.0519 BTU/lb-°F
	0.255 J/g-°C	0.0609 BTU/lb-°F
Thermal Conductivity	138 W/m-K	958 BTU-in/hr-ft <sup>2</sup> -°F
	100 W/m-K	694 BTU-in/hr-ft <sup>2</sup> -°F
	@Temperature 1127 °C	@Temperature 2061 °F
	105 W/m-K	729 BTU-in/hr-ft <sup>2</sup> -°F
	@Temperature 927 °C	@Temperature 1700 °F
	112 W/m-K	777 BTU-in/hr-ft <sup>2</sup> -°F
	@Temperature 727 °C	@Temperature 1340 °F

## Thermal Properties

	118 W/m-K @Temperature 527 °C	819 BTU-in/hr-ft <sup>2</sup> -°F @Temperature 981 °F
	126 W/m-K @Temperature 327 °C	874 BTU-in/hr-ft <sup>2</sup> -°F @Temperature 621 °F
	130 W/m-K @Temperature 227 °C	902 BTU-in/hr-ft <sup>2</sup> -°F @Temperature 441 °F
	134 W/m-K @Temperature 127 °C	930 BTU-in/hr-ft <sup>2</sup> -°F @Temperature 261 °F
	138 W/m-K @Temperature 27.0 °C	958 BTU-in/hr-ft <sup>2</sup> -°F @Temperature 80.6 °F
	143 W/m-K @Temperature -73.0 °C	992 BTU-in/hr-ft <sup>2</sup> -°F @Temperature -99.4 °F
	150 W/m-K @Temperature -263 °C	1040 BTU-in/hr-ft <sup>2</sup> -°F @Temperature -441 °F
	179 W/m-K @Temperature -173 °C	1240 BTU-in/hr-ft <sup>2</sup> -°F @Temperature -279 °F
	210 W/m-K @Temperature -193 °C	1460 BTU-in/hr-ft <sup>2</sup> -°F @Temperature -315 °F
	250 W/m-K @Temperature -213 °C	1740 BTU-in/hr-ft <sup>2</sup> -°F @Temperature -351 °F
	280 W/m-K @Temperature -253 °C	1940 BTU-in/hr-ft <sup>2</sup> -°F @Temperature -423 °F
	350 W/m-K @Temperature -233 °C	2430 BTU-in/hr-ft <sup>2</sup> -°F @Temperature -387 °F
Melting Point	2617 °C	4743 °F
Boiling Point	4639 °C	8382 °F
Heat of Formation	0.000 kJ/mol	0.000 kJ/mol
	658.1 kJ/mol	658.1 kJ/mol

## References

**CRC Handbook of Chemistry and Physics**, Robert C. Weast, Ed. 62 Edition, CRC Press, Boca Raton, FL, 1981.

**Metallic Materials Specification Handbook**, Fourth Ed., Robert B. Ross, Chapman & Hall, London, 1992

**Metals Handbook**, Vol.2 – Properties and Selection: Nonferrous Alloys and Special-Purpose Materials, ASM International 10th Ed. 1990.

**The Metals Databook**, Alok Nayer, McGraw-Hill, New York, 1997.

**CRC Handbook of Chemistry and Physics**, David R. Lide, Ed. 80th Edition, CRC Press, Boca Raton, FL, 1999.